

Ophthalmic Testing Report

Report Number: R-20160606-034 Contact Angle


Prepared for:

Chiaro a Gradus Group Company 375 West 35th Street New York, NY 10001

June 15, 2016

NSL Analytical Services, Inc. NSL Analytical 4450 Cranwood Parkway Cleveland, Ohio 44128 Phone: 216-438-5200

Fax: 216-438-5050





Contact Angle Page 2 of 4 June 15, 2016

Contents

Project Definition and Scope	. 3
Sample Identification	. 3
Opinions, Interpretations, and Conclusions	. 3
Results	. 4
Table 1: Contact Angle, S-160606-054_059	. 4



Page 3 of 4 June 15, 2016

Project Definition and Scope

Twelve lens filters were submitted for Contact Angle measurement. The test outlined was performed on all samples. The samples were received on June 6, 2016.

Sample Identification

The samples are labeled as indicated in the table below.

Sample Number	Client Label	Pass/Fail
S-160606-054	Class A (99-UVBTS72)	Pass
S-160606-055	Class AB (99-UVBT72)	Pass
S-160606-056	Class B (98-UVATS72)	Pass
S-160606-057	New Class C (98-UVAT72)	Pass
S-160606-058	Class D (95-UVAT72)	Fail
S-160606-059	Class E (90-UVAT72)	Fail

Opinions, Interpretations, and Conclusions

If you have any questions regarding these results, please contact us.

Report Prepared By: Terry Graham Ophthalmic Technician

Approved by:



Report #: R-20160606-034 Contact Angle Page 4 of 4 June 15, 2016

Results

Table 1: Contact Angle, S-160606-054_059

R-20160606-034		Sample #:	S-160606-054_0	=-
1 0 0010			3-100006-034_0	59
June 9, 2016		Manufacturer:	Gradus Group, LLC	
TG		Material:	N/A	
ı		Coating:	N/A	
Descriptive Marks	Contact Angle	Pass: ≥110.0	Contact Angle	Pass: ≥110.0 Fail: <110
	119.7	Pass	118.5	Pass
, ,	120.9	Pass	121.8	Pass
Class AB (99-UVBT72)	122.1	Pass	118.8	Pass
·	122.7	Pass	119.3	Pass
Class B (98-UVATS72)	121.5	Pass	120.8	Pass
	123.1	Pass	122.8	Pass
New Class C (98-UVAT72)	121.6	Pass	120.9	Pass
	121.1	Pass	121.8	Pass
Class D (95-UVAT72)		Fail		Fail
				Fail
Class E (90-UVAT72)				Fail
	38.8	Fail	37.0	Fail
ents:				
	Descriptive Marks Class A (99-UVBTS72) Class AB (99-UVBT72) Class B (98-UVATS72) New Class C (98-UVAT72) Class D (95-UVAT72) Class E (90-UVAT72)	Descriptive Marks Class A (99-UVBTS72) 119.7 120.9 122.1 122.7 121.5 123.1 New Class C (98-UVAT72) 121.6 121.1 Class D (95-UVAT72) 43.2 30.7 Class E (90-UVAT72) 48.7 38.8 120.0	TG Descriptive Marks Class A (99-UVBTS72) Class AB (99-UVBT72) Class B (98-UVAT72) Class C (98-UVAT72) Class C (98-UVAT72) Class C (98-UVAT72) Class D (95-UVAT72) Class D (95-UVAT72) Class E (90-UVAT72)	TG Material: N/A